



"If you can imagine it, Nadco will make it stick."

PE350 WHITE

PRODUCT DATA

	VALUE	TEST METHOD
Physical Properties		
Thickness: (mils[microns])	Film	3.4 (86) +/- 10%
	Adhesive	0.5-0.6 (13-15) +/- 0.1 (3)
	Liner	1.2 (30) +/- 5%
Dimensional Stability (%)	MD	0.75
	TD	0.50
Adhesion Properties		
Ultimate Peel from	Average	ASTM D 903 (Modified for 72 hour dwell time)
	Oz/in (N/m)	
Acrylic	61 (671)	
Aluminum	75 (825)	
Glass	66 (726)	
Painted Metal	51 (561)	
Painted Plastic	28 (308)	
Polyester	47 (517)	
Polyethylene	34 (374)	
Polyethylene Corona Treated	51 (561)	
Polypropylene	21 (231)	
PVC	58 (638)	
Stainless Steel	62 (682)	
Expected Shear		ASTM D 3654 Method A a. 1 hr. dwell b. 1 sq.in. surface c. 4 lb. load
Room Temp (hours)	10	
Tack (gm/sq cm)	500	ASTM D 2979
Expected Exterior Life	Indoor use only	
Service Temperature Range	-40°F to 176°F (21°C) and 50% relative humidity	