



"If you can imagine it, Nadco will make it Stick."®

7719 Smooth Cling Film

Product Description

Nadco® Smooth Cling Films utilize a unique acrylic adhesive system that allows the adhesive to flow on to a surface with little to no application pressure. The self wetting adhesive is nearly ultra-clear which provides excellent transparency. These protective label stocks are ideal for use in many industrial and commercial applications. Some typical applications include: printed window advertisements and protecting mobile handheld displays during shipment from the manufacturer to end user, printed clear labels, protective overlaminates, and surface protection.

Construction

Product	Face Stock	Adhesive	Release Liner
Smooth Cling Film 7719	5 mil (0.127 mm) Clear PET	1 mil (0.025 mm) 1200 Adhesive (Low Adhesion)	2 mil (0.5 mm) White PET

***Note:** The caliper listed is based on a calculation from manufacturing controlled adhesive coat weights using a density of 1.012 g/cc.

Features

- Ultra-clear, high transparency film and adhesive combination – suitable for display panels.
- Removable adhesive – easily removable from many surfaces with no adhesive residue.
- PET lined product allows for die-cutting to any shape and is suitable for high-speed, automatic dispensing.
- PET face material – much higher temperature resistance than PE protective Films.
- Before application the surfaces must be free from oil, fat, dust and solvents. Best results are achieved when applied between 50°F and 104°F.
- The product has a high transparency (low haze).
- The adhesive is cleanable with water so it may be re-used.

Application Ideas

- Protect window apertures and displays in electronics applications.
- Temporary protection of sensitive surfaces against dirt, dust and damage during processing, storage and mounting etc.
- Low level of adhesion and is suitable for protection of many surfaces including: Glass, Varnished / hardcoated surfaces, Aluminum and Plastic surfaces.
- Printed window film and advertisements

Typical Physical Properties

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

90° Peel Adhesion (20 minute dwell, 12 in./min. [305 mm/min])

Smooth Cling Films	Stainless Steel		Glass		Polycarbonate	
	g/in.	g/25.4 mm	g/in.	g/25.4 mm	g/in.	g/25.4 mm
7719	25	25	25	25	10	10

Liner Release

Smooth Cling Films	g/in.	g/25.4 mm
7719	20	20

Optics (without liner) ASTM D1003
Haze <2% Typical

Environmental Aging Tests

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Environmental Aging to glass. Tests carried out at conditions noted below. After test samples left at standard conditions for 2 hours, then evaluated. Standard conditions are 23°C and 50% relative humidity.

Smooth Cling Films	16 hours at -40°F		16 hours at 185°F		Temperature cycling. -40°F 2 hr. 185°F 2 hr. (5 cycles)		Temperature and humidity cycling. 90°F 90% RH 2 hr. -131°F 2 hr. (6 cycles)	
	g/in.	g/25.4 mm	g/in.	g/25.4 mm	g/in.	g/25.4 mm	g/in.	g/25.4 mm
7719S	10	10	40	40	10	10	5	5

Printing

The polyester film is designed with a printable surface suitable for printing instructions, promotional messages or bar codes via thermal transfer and conventional flexographic printing methods.

Storage

Store at room temperature conditions of 72°F (22°C) and 50% relative humidity.

Shelf Life

If stored under proper conditions, product retains its performance and properties for one year from date of manufacture.



Technical Information

The technical information, recommendations and other statements contained in this document are based upon tests or experience that Nadco® believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Product Use

Many factors beyond Nadco® control and uniquely within user's knowledge and control can affect the use and performance of a Nadco® product in a particular application. Given the variety of factors that can affect the use and performance of a Nadco® product, user is solely responsible for evaluating the Nadco® product and determining whether it is fit for a particular purpose and suitable for user's method of application.

**Warranty,
Limited Remedy,
and Disclaimer**

Unless an additional warranty is specifically stated on the applicable Nadco® product packaging or product literature, Nadco® warrants that each Nadco® product meets the applicable Nadco® product specification at the time Nadco® ships the product. Nadco® MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the Nadco® product does not conform to this warranty, then the sole and exclusive remedy is, at Nadco® option, replacement of the Nadco® product or refund of the purchase price.

Limitation of Liability

Except where prohibited by law, Nadco® will not be liable for any loss or damage arising from the Nadco® product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.