

"If you can imagine it, Nadco will make it stick."

79449

Destructible Satin Vinyl/S730/50#SCK

(Standard shelf life is amended to 6 months from date of purchase when stored at 70°F/50% R.H.)

Facestock	Facestock physical properties					
2 Mil destructible			Imperial	Units	Metric	Units
Vinyl is a satin white cast			value		value	
vinyl film designed	Caliper:		0.0020		50.80	micron
specifically for security	ASTM D1000					
labeling. Care should be	Tensile:	MD	5	psi	0	
taken in qualifying a	ASTM	1,12		Por		
particular die	D882	CD	5	psi	0	
configuration to ensure proper strippability.	D002	CD		psi	O .	
Standard shelf life is						
amended to 6 months						
from date of purchase						
when stored at 70°						
F/50% R.H.						

Adhesive	Adhesive physical properties						
S730 is a clear solvent acrylic permanent			Imperial value	Units	Metric value	Units	
adhesive for general	Type:		Solvent acrylic				
purpose industrial applications. Features good initial tack and ultimate adhesion to a wide variety of substrates including medium to low surface energy plastics, and high shear for minimal cold flow or ooze characteristics.	Caliper: ASTM D1000		0.0009	inches	22.86	micron	
	Standard Coat Wt:				27	g/sq m	
	Minimun Appl Temp:		50	°F	10	°C	
	Service	Min	-40	°F	-40	°C	
	Temp Range:	Max	300	°F	149	°C	
	Loop Tack S Steel: PSTC1		59.2	Oz/inch	65.1	N/100 mm	



"If you can imagine it, Nadco will make it stick."

Liner		Liner physical properties					
50#SCK is a bleached, super calendered kraft			Imperial value	Units	Metric value	Units	
paper liner with very good diecutting and matrix stripping properties. Supplied with an anti-block coating on the backside of the liner to control ad hesive and label transfer to the backside of the liner in finished, wound rolls. This liner	Caliper: ASTM D1000		0.0032	inches	81.2800	micron	
	Basis Wt: TAPPT T410 *(24" x 36" 500 sheets)		54.0	Lbs/ream	86.4	g/sq m	
	Tensile: ASTM	MD	48.0	lbs/inch	211.2	N/25 mm	
should not be used in fanfolded label	D882	CD	26.0	lbs/inch	114.4	N/25 mm	
applications, and is not recommended for back printability.	Tear:	MD	1.7	ounces	48.3	grams	
	TAPPI T414	CD	2.0	ounces	56.8	grams	

Liner Release: TMLI 90° removal of liner from facestock	Total construction caliper (approximate):	
Rate of removal	Grams/2" width	
400 inches/min.	20	0.0063 inches (6.3 mils; 160 microns)

Features and Benefits

Opaque white satin vinyl with excellent hiding power.

Fragile facestock tears very easily for tamper evidence.

Clear acrylic general purpose permanent adhesive with good adhesion to most metals, paints, and plastics.

Inherently flexo printable surface

Anti-block coating on the back of the liner.

Note: Although the adhesive is suitable for use up to 300°F, the facestock is limited to 225°F

Applications and Uses

Security labels and seals

Tamper-proof or tamper evident labels

Warranty labels

Authentication marks

Printing and Converting

Destructible vinyl is printable with most standard flexographic and UV letterpress inks. For specific diecutting requirements consult the Technical Marketing Bulletin for material. Due to manufacturing requirements, there might be a maximum of 15 splices per 1,668 yards. It is strongly recommended that the product be converted and applied to substrate within 6 months of purchase. Due to inherent properties of this unique product, facestock shrinkage does occur. Exposure to environmental conditions other than those recommended will accelerate facestock shrinkage or liner growth. Either condition can make the product unusable. Not recommended for automatic application.



"If you can imagine it, Nadco will make it stick."

RoHS/Regulation 2002/95/EU

The substances listed in article 4 lid 1 of 2002/95/EU (RoHS) are not intentionally used in this product. The concentration limits of these substances willnto exceed the set maximum concentration limits as provided in the proposed amendment for 2002/95/EU.

Optimal storage conditions

Unless otherwise specified in this document, ideally stores at 72F and 50% RH

Note:

The technical data presented is from tests we believe to be reliable but should be considered representative or typical only and should not be used for specifications purposes. This product should be tested thoroughly under end-use conditions to ensure it meets the requirements of the specific application.

Appendix

Performance Date:

The following technical data should be considered representative or typical only and should not be used for specification purposes. This data was obtained with the adhesive applied to 2 mil polyester facestock. It is not possible to conduct these tests with this facestock due to the fragile nature of the facestock.

		nitial ute dwell)		2 Hours at Room 72 Hours at 120°F emperature		96 Hours at 150°F (65°C) & 80% Relative Humidity		
Surface	Oz/in	N/100mm	Oz/in	N/100mm	Oz/in	N/100mm	Oz/in	N/100mm
1.Aluminum	77.1	84.8	70.2	77.2	86.2	94.8	112.6	123.9
2.Stainless Steel	67.7	74.5	84.8	93.3	90	99	124.3	136.7
3. ABS Plastic	58.9	64.8	77.8	85.6	73.3	80.6	54.6	60.1
4. Polypropylene	24	26.4	0	0	11	12.1	1	1.1
5.HDPE	11.7	12.9	4.4	4.8	11	12.1	20.5	22.6
6.LDPE	11	12.1	13.2	14.5	8.8	9.7	1.4	1.5



"If you can imagine it, Nadco will make it stick." $_{\circledR}$

Environmental Performance: Chemical resistance test results

The performance results are based on 4 hour immersions at room temperature unless otherwise noted (gasoline is 1 hour). Samples were applied to stainless steel and conditioned for 24 hours before immersion and evaluated immediately upon removal. Adhesion measured at 180° peel.

	Adhesion to Stainless Steel		Visual	Edge	
Chemical	Oz/in	N/100mm	Appearance	Penetration mm	
1.70% IPA	81.5	89.7	No change	0	
2.Tide Detergent	72.5	79.8	No change	0	
3. Engine Oil (10W30	76.8	84.5	No change	0	
4. Water	36.7	40.4	No change	0	
5. Ammonia	29.6	32.6	No change	0	
6. 409 Cleaner	38.7	42.6	No change	3.1	
7. Toluene	33.7	37.1	No change	6.4	
8. Brake Fluid	79.4	87.3	No change	0	
9. Reference Fuel C	50.72	55.8	No change	3.3	
10. Kerosense K1	69	75.9	No change	3.1	
11. Heptane	60.7	66.8	No change	0	

Compliance Recognition:

409 is a registered trademark of the Clorox Company Tide is a registered trademark of the Procter & Gamble Company

The information on compliance conditions, substrates, and printing products contained in the tables above represent a summary of recognized or acceptable conditions and printing products. Other conditions, substrates, and printing products may be recognized with this material. Please consult the specific compliance organization records or specific files for a completer listing.