



"If you can imagine it, Nadco will make it Stick."

HO51 WHITE POLYESTER

Product Data Sheet

2.0 mil White Polyester / Heavy Coat Weight AT Adhesive / 50# sck Liner

Facestock(2.0 mil White Polyester): A 2.0 mil bright white bopp with a 52% gloss level. Outstanding whiteness and opacity. Chemically treated for printability using standard print methods and thermal transfer (with resin ribbon only). This film has high machine direction stiffness and tensile strength for superior high speed label dispensing. This film is water resistant and very durable.

Type:	Film	Basis Weight:	N/A		<u>Federal Regulation</u> <u>Approval</u>	_
Caliper:	2.0 mil	Tensile:	MD: 21000 N/mm2	TD: 31000 N/mm2	Heavy Metals:	Yes
					Toy Safety:	Yes
Opacity:	90.0 %	Tear:	MD: N/A	CD: N/A	Indirect Food:	Yes
Brightness:	N/A	Elongation:	MD: 160%	CD: 090%	Direct Food:	No

Adhesive(**Heavy Coat Weight AT**): An outstanding all temp and freezer grade acrylic permanent adhesive which has high initial tack and high ultimate adhesion. It is used for freezer labels. outdoor applications, and many other difficult to label items.

Coat Weight:	Heavy	<u>Federal Regulation</u> <u>Approval</u>		Typical Adhesion Values	
	Permanent			Stainless Steel:	
Adhesive Type:	Acrylic	Heavy Metals:	Yes	180° Peel:	1.40 lbs/in
	35 minutes	Toy Safety: Indirect Food:	Yes Yes	Loop Tack:	1.80 lbs/in ²
Shear:				Glass:	
		Direct Food:	No	10 min dwell:	1 lb/in
Minimum Application Temperature:	-20° F			Polyethylene:	
Camilaa	-65° F to 160° F			10 min dwell:	3.0 lb/in
Service Temperature:				Corrugated:	
•	No			10 min dwell:	4.3 lb/in
ACTS Approval:				Painted Metal:	
				10 min dwell:	4.3 lb/in

Release Liner(50# sck): A general purpose release liner which has been silicone coated one side to give a controlled release. This paper has a smooth, caliper contistent surface. Due to its high internal strength it will withstand all conventional processing operations including die-cutting, butt cutting, line scoring and dispensing.

Basis Weight: 50 lb/ream Tensile: CD:

Caliper: 3.2 mil **Release**: Target: 15 -50 g 2" at 180° 300ipm)

WARRANTY: All data obtained through ASTM standards and are typical and should not be used for specification purposes. Because of the variety of possible uses, the buyer should test the suitability of each intended use. The buyer assumes all risks in connection with such use. Please see oure web site for terms and conditions. WWW.NADCOINC.COM