

"If you can imagine it, Nadco will make it stick."

# **PVC Industrial Foam**

**PVC Industrial Foam** is engineered to provide a cost-effective solution to your most demanding sealing and cushioning requirements. This closed cell polyvinyl chloride foam can be produced with or without adhesive.

### PERFORMANCE CHARACTERISTICS

- Remains flexible at 20° C-to 80° C
- Resistant to most solvents and chemicals
- Fire resistant per FMVSS 302
- Ultraviolet resistant
- Seals out light, air, dust and moisture
- · Cushions against vibration and noise

#### **ADHESIVE**

- Water-based acrylic
- · Good initial tack and high shear
- Excellent resistance to plasticizers
- Builds bond strength over time
- Recommended for most industrial applications

### **INDUSTRIES**

- Transportation
- General Assembly
- Appliance
- Construction
- HVAC
- Retail
- Industrial

## **SUBSTRATES**

- 90 # paper
- 2.0 mil polyester film
- 1.5 mil aluminum

### **COLORS**

Standard

Special (minimums apply)

- Black
- White

- Gray
- BrownNatural
- Charcoal
- Custom Colos

Characteristic	Sof-Seal	Low Density	Medium Density	High Density	Very High Density
Thickness	1/16" – 3/4"	1/16" — 1"	1/16" – 1/2"	1/16" — 1/2"	1/32" — 1/16"
Length *	6 – 300 ft.	7 – 300 ft.	10 – 300 ft.	10 – 300 ft.	50 – 300 ft.

<sup>\*</sup>The availability of log lengths is dependent upon foam thickness.

Physical Property	Test Method	Sof-Seal	Low Density	Medium Density	High Density	Very High Density
Density (lbs./cu. ft.)	ASTM D1667	5	7	11	15	19
Shore Hardness "00"	ASTM D2240	5	25	43	53	58
Force to Compress 25%		1.4 psi	3.6 psi	7.0 psi	10.2 psi	12.0 psi
Compression Deflection	ASTM D1667	0.5 psi	1.3 psi	4.0 psi	6.0 psi	7.0 psi
Water Absorption	ASTM D1056	3 %	3 %	2 %	2 %	1 %
Tensile Strength	ASTM D412	15 psi	30 psi	40 psi	70 psi	90 psi
Elongation	ASTM D412	275 %	190 %	150 %	150 %	160 %

**SHELF LIFE** Foam Seal PVC Foam has a shelf life of two (2) years from the date of manufacture without adhesive and six (6) months with adhesive, as indicated by the lot number, when stored at or below 75° F.