



"If you can imagine it, Nadco will make it Stick."®

OVM
MATTE POLYPROPYLENE OVERLAMINATE

Features and Applications

Excellent acid, chemical, oil and scuff resistance.
 Soft non-glare finish is receptive to pen, pencil or marker.
 Ideal for beverage, food and cosmetic labels where an attractive, high end appearance is desired.

Physical Properties

Film	1 mil Matte Biaxially Oriented Polypropylene (BOPP)
Adhesive	0.5 mil High Grade Clear Emulsion Acrylic
Total Construction	1.5 mil +/- 10%

Typical Technical Values

	Value	Test Method
Film Elongation at Break	190% MD 70% TD	ASTM D882
Adhesion to Steel	13 oz/in 30 min conditioning 15 oz/in 24 hr conditioning	180° peel at 12 in/min 180° peel at 12 in/min ASTM D3330/D3330M-04
Unwind Adhesion	11 oz/in 30 min conditioning	180° peel at 12 in/min ASTM D3811/D3811M-96
Service Temperature Range	0°F to 180°F	
Application Temperature	32°F to 150°F	

Roll Tolerances

Roll Length	+/- 5%
Roll Width	+/- 0.0625 in (1/16 th in)

Storage and Handling

Two years when stored at 70°F and 50% relative humidity.
 Rolls must be transported and stored on protected surfaces.
 Use caution when placing or removing roll from mandrel.

Regulatory Compliance

RoHS, RoHS2, REACH, TSCA, Toy Safety Standard ASTM F963, CEPA, CONEG, FDA 21CFR175.105, 21CFR177.1520(c) (1.1) & (3.1). California Proposition 65

Product Performance and Suitability

We believe the statements and information contained herein are accurate but are to be used only as general guidelines and are not warrants or guarantees. Because of the variety of possible uses, there is no warranty of fitness for a particular purpose. This product may not be suitable for use on metallic or dark reverse printed labels. The buyer must test the suitability for each intended application before using. NADCO® will not be liable for damages in excess of the purchase price of its products or for incidental or consequential damages. NADCO® warrants its products to be free from defects in material and workmanship. Should any failure to conform to this warranty appear within one year of the initial date of shipment, NADCO® shall, upon notification thereof and substantiation that the products have been stored and applied in accordance with NADCO®'s standards, correct such defects by suitable repair or replacement without charge at NADCO®'s plant or at the location of the products (at NADCO®'s election); provided, however, if NADCO® determines that repair or replacement is not commercially practical, NADCO® shall issue a credit in favor of the buyer in an amount not to exceed the initial purchase price of the product from NADCO®.